

# SOLE

## **Expansion 1.25**

L

## Technical Information

### **Product description**

Designed for the footwear segments crosslinkable and foam compounds primarily based on EVA. It is to be had in many colorations.

#### Storage conditions

The material must be stored in closed and undamaged bags, at dry places not exceeding 30 °C, avoiding direct exposure to sunlight and weathering. With these storage conditions the shelf life of the material is six months.

Physical information	TEST METHOD		Value	Tolerance	Unit
Density	ISO 2781		0,48	±0,03	g/cm³
Hardness Information					
	ISO 868		48	±3	Shore A
Durometer Hardness					
	ASTM D2240		65	±3	Asker C
Mechanical Properties					
Tensile strength	ISO 37	without skin	4,5	≥	mPa
Elongation at break	ISO 37		300	≥	%
Tear strength	ISO 34 Met. A	without skin	5,5	2	kN/m
Abrasion	ISO 4649	10N – 40cm	200	≤	mm <sup>3</sup>
Shrinkage	Internal method	24h at 70ºC	6	≤	%
Expansion rate	Internal method		125	±0,5	%
Processing Information			Value		
First barrel zone			85-95		°C
Second barrel zone		85-95	85-95		
Third barrel zone			85-95		°C
Head of the barrel			90-100		°C
Mould temperature	175-185			°C	
Curing time			420-480		S

The processing information provided for informational purposes. Temperatures, climate conditions, pressure and time are strongly influenced by the equipment and the mould construction and must be controlled manner during injection moulding process.

For any further information please contact info@evacare.com.tr

EVACARE

Giyim Koop. Sanayi Sitesi, Deposite Outlet İş Mrk. Depo Katları 5A/6A Blok. Kat:4 No: 410, 34490

Başakşehir/İstanbul, Türkiye

Tel: +90 212 243 64 55 E-mail: info@evacare.com.tr

https://www.evacare.com.tr